

DX62

2K HS PRODUCTIVE PRIMER

Description

Extremely fast drying, 2-component high solids primer.
Colour: medium grey.
Composition based on functional acrylic copolymer.

Products

| | |
|------|-------------------------|
| DX62 | 2K HS Productive Primer |
| DX25 | Activator |
| DX20 | Standard Activator |
| DX22 | HS Activator Fast |
| DX24 | Activator Extra Fast |
| DX32 | Thinner Fast |
| DX34 | Standard Thinner |

Properties

- Easy to apply, smooth flow.
- Very high productive primer: easy wet and dry sandability after 1 hr air dry, very short flash time between coats.
- Very easy to sand, many days after application.
- Superb filling.
- Can be coated with DUXONE[®] topcoat.









Substrates

- OEM finishes.
- Cured repair finishes.
- Sanded putties.
- Primed steel, zinc galvanised steel and aluminium.
- DUXONE[®] 1K Primer Filler DX61.

DX62

2K HS PRODUCTIVE PRIMER

PRODUCT PREPARATION

| | | | | | | | | | |
|--|--------------------------------|---|-------------------------------|--------|---|--------|--------------------|--------|--|
|  | Mixing ratio | | Standard (DX25) | | Standard/Fast (DX20/DX24) | | Fast (DX22) | | |
| | | DX62 | Volume | Weight | Volume | Weight | Volume | Weight | |
| | | DX25 | 3 | 100 | 4 | 100 | 6 | 100 | |
| | | DX20/DX24 | 1 | 24 | - | - | - | - | |
| | | DX22 | - | - | 1 | 18 | - | - | |
| | DX32/DX34 | - | - | - | - | 1 | 12 | | |
| | | - | - | 0.5 | 8 | 1 | 11 | | |
| | VOC | 520 g/l | | | | | | | |
|  | Pot life at 20°C | DX20/DX25 DX22/DX24 | 1 hr - | | 1 hr 30 min | | - 30 min | | |
|  | Spray viscosity at 20°C | DIN 4 FORD 4 AFNOR 4 | 22-28 s 22-28 s 24-30 s | | | | | | |
|  | Spray equipment | | Fluid tip | | Distance | | Pressure | | |
| | | Conventional guns | | | | | | | |
| | | Gravity feed | 1.4-1.8 mm | | 20-25 cm | | 3-4 bar | | |
| | | Suction feed | 1.6-1.8 mm | | 20-25 cm | | 3-4 bar | | |
| | | Pressure feed | 1.0-1.2 mm | | 20-25 cm | | 3-4 bar | | |
| Compliant guns (HVLV/HTE) | | | | | | | | | |
| Gravity feed | 1.4-1.7 mm | | 15-20 cm | | According to supplier's specifications | | | | |
| Suction feed | 1.6-1.8 mm | | 15-20 cm | | | | | | |
| Pressure feed | 1.0-1.2 mm | | 15-20 cm | | | | | | |
|  | Number of coats | 1-3 | | | | | | | |
|  | Flash time | Between coats till flat. 10 min before bake. | | | | | | | |
| | DFT | 50-100 μ | | | | | | | |
|  | Dry to sand | | DX20/DX25 | | DX24 | | DX22 | | |
| | | at 15°C | 2-3 hr | | 1-2 hr | | 1-2 hr | | |
| | | at 20°C | 1-2 hr | | 1 hr | | 1 hr | | |
| | | at 40°C | 30-40 min | | 30 min | | 30 min | | |
| | | at 60°C | 30 min | | 20 min | | 25 min | | |
|  | IR drying* | Distance | 80 cm | | * Guideline for short/medium wave IR equipment. | | | | |
| | | Half power | 5 min | | | | | | |
| | | Full power | 10-15 min | | | | | | |
| This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use. | | | | | | | | | |

DX62

2K HS PRODUCTIVE PRIMER

RECOMMENDED USE

Surface preparation

- Before applying DX62, clean the surface, sand and degrease properly.

Equipment cleaning

Use a correct solventborne gunwash.

Remarks

- Do not use activated DX62 beyond the pot life nor reduce it further to get viscosity down again.
- For faster drying and/or at low temperatures DX62 can be activated with DX22 in volume ratio 4 to 1.
- If DX62 is applied over thermoplastic acrylic finishes, complete panel or overall car has to be treated. Spot repairing or sand throughs of the primer can result in spot marking or lifting when applying a basecoat.
- Do NOT exceed recommended film thickness to avoid film defects, poor film through cure and poor adhesion.
- Respect mixing ratios, drying times, spray pressure and DFT to avoid poor sandability and paperfilling.
- Activated material should not be returned to original can of non-activated material.
- Close can of activator tightly immediately after use, as this product will react with humid air and water and lose its hardening effect.
- Material has to be at room temperature (18-25°C) before use.

DX62

2K HS PRODUCTIVE PRIMER

RECOMMENDED USE (con'd)

Product data

Package viscosity: 2500-3000 cp (at 5 rpm)
900-1200 cp (at 20 rpm)
Theoretical coverage: 7 m²/l at 50 μ DFT - ready-to-spray

| Products | Packages (l) | Shelf life at 20°C (year) | Density (kg/l) |
|----------|-----------------|------------------------------|-------------------|
| DX62 | 1 | 2 | 1.330 |
| DX20 | 0.25 - 0.5 - 1 | 2 | 0.959 |
| DX22 | 0.25 - 0.5 - 1 | 2 | 0.986 |
| DX24 | 0.5 - 1 | 2 | 0.962 |
| DX25 | 0.5 | 2 | 0.949 |
| DX32 | 1 - 5 | 2 | 0.874 |
| DX34 | 1 - 5 | 2 | 0.903 |

Safety

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.